

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C04B 24/12	A1	(11) International Publication Number: WO 95/04010 (43) International Publication Date: 9 February 1995 (09.02.95)
(21) International Application Number: PCT/US94/07948 (22) International Filing Date: 14 July 1994 (14.07.94) (30) Priority Data: 08/099,089 29 July 1993 (29.07.93) US (71) Applicant: W.R. GRACE & CO.-CONN [US/US]; 1114 Avenue of the Americas, New York, NY 10036 (US). (72) Inventors: ABDELRAZIG, Baha, Eldin, Ismail; 33 Shalcross Crescent, Hatfield, Hertfordshire AL10 9QH (GB). GARTNER, Ellis, Martin; 1105 Tanley Road, Silver Spring, MD 20904 (US). MYERS, David, Francis; 10920 Rock Coast Road, Columbia, MD 21044 (US). (74) Agent: TROFFKIN, Howard, J.; W.R. Grace & Co.-Conn., 7379 Route 32, Columbia, MD 21044 (US).		(81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LT, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, TJ, TT, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: A LOW SHRINKAGE CEMENT COMPOSITION (57) Abstract A cement composition capable of inhibiting drying shrinkage and cracking resulting therefrom composed of cement and an alkyl or cycloalkyl carbamate, an alkylene dicarbamate, polyoxyalkylene dicarbamate or mixtures thereof.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

A LOW SHRINKAGE CEMENT COMPOSITION

BACKGROUND OF THE INVENTION

The present invention is directed to a cement composition admixture capable of reducing drying shrinkage and cracking resulting therefrom.

One of the major disadvantages of conventional cement compositions is that they tend to shrink during curing of the composition. This shrinkage results in cracks, and other defects in the resultant structure. Such cracks have both appearance and physical defects to the structure. For example, water can enter in the cracks and further deteriorate the structure through freeze-thaw pressures exerted by the water on the cement composition.

Various admixtures have been suggested as useful in reducing drying shrinkage and the resultant cracking. Japanese Patent Laid-Open Application 81/37259 and Japanese 87/10947 disclose the use of alcohol-alkylene oxide and alkylphenol-alkylene oxide adducts as useful for this purpose. However, these materials must be used in large dosages which causes their usage to be too expensive for practical use. C₄-C₆ alkyl alcohols, as disclosed in U.S. 5,181,961, have been suggested for use in inhibiting drying shrinkage. However, the alcohols are not highly effective under dry conditions and they tend to leach out under any wet condition encountered. In addition the lower alcohols have high vapor pressure at ambient conditions and are, therefore, difficult to handle.


A need continues to exist for a cement composition admixture and a resultant cement composition capable of inhibiting drying shrinkage. The admixture must be inexpensive, readily handleable at the job site and

- 2 -

provide the desired inhibiting effect at low dosage levels.

SUMMARY OF THE INVENTION

The present invention provides a cement composition, capable of inhibiting drying shrinkage to cement compositions. The admixture provides the desired result under various environment conditions, can be used in low dosages and is readily handled at the job site. The subject admixture comprises at least one compound of the formula



wherein R represents a C₃-C₈ alkyl group or a C₅-C₆ cycloalkyl group when n is 1 or a C₂-C₁₀ alkylene group or a group having the formula A(OA)_xOA wherein each A is a C₂-C₃ alkylene and x is an integer of from 0 to 10 when n=2.

DETAILED DESCRIPTION OF THE INVENTION


It has been presently found that carbamates, as fully described herein below, are compounds capable of inhibiting drying shrinkage and the resulting stress cracks normally encountered in cement compositions.

Cement compositions undergo a sequence of stages during its complete curing process. From the initial hydration of the cement until set, the mass undergoes certain dimensional changes, including plastic shrinkage. The mass can, however, substantially overcome and correct for the stresses which occur at this stage. However, subsequent to set, the mass undergoes further dimensional changes which are called dry changes, including drying

- 3 -

shrinkage. Although these changes are small in magnitude, they give rise to internal and external stresses which result in the formation of permanent cracks and deformations to the mass.

5 The admixture unexpectedly found to inhibit dry shrinkage is composed of at least one compound represented by the formula:



10 wherein R is a C₃-C₈ alkyl group, or C₅-C₆ cycloalkyl group when n is 1 or a C₂-C₁₀ alkylene or an oxyalkylene A(OA)OA group with x being 0 to 10, when n is 2.

15 In the above formula, typical examples of the alkyl group represented by R include n-propyl, isopropyl, n-butyl, iso-butyl, tertbutyl, n-pentyl, iso-pentyl, 1,2-dimethyl butyl, 1,3-dimethyl butyl, 2,2-dimethyl propyl, tert-pentyl, n-hexyl, iso-hexyl, 2-methyl pentyl, 3-methyl pentyl, 4-methyl pentyl, 2,2-dimethyl butyl, 3,3-dimethyl butyl and 2,3-dimethyl butyl; and typical
20 examples of the cycloalkyl group represented by R include cyclopentyl, cyclohexyl and methyl cyclohexyl. Among these groups, the most preferred group is a butyl group.

25 Examples of the divalent R groups are alkylene groups, such as ethylene, propylene, 1-methyl-ethylene, hexylene and the like; and alkyleneoxyalkylene (AOA) or polyoxyalkylene -A(OA)_xOA- groups such as -CH₂CH₂OCH₂CH₂-; -CH₂CH₂CH₂OCH₂CH₂CH₂-; or -CH₂CH₂(OCH₂CH₂)_xOCH₂CH₂- and the like. Among these groups, the most preferred are
30 ethylene, propylene, and ethyleneoxyethylene.

The present cement composition admixture are solids or liquids which can be readily transported and either dispersed in water or water-alcohol media or made

- 4 -

solutions therewith. Thus, the subject admixtures can be introduced into and made part of a dry mix of cement and the subject admixture. Such mixtures can be formed with from about 90 to 99 weight percent cement and 1 to 10 (preferably 1 to 5) weight percent of the present admixture. Alternately, the present admixture can be added (either in its solid state or as a dispersion) as part of the mixing of components used in forming the cement composition. For example, a preferred alkyl carbamate, n-butylcarbamate, is a solid. It can be readily mixed with conventional portland cement to form a dry powder blend which when later hydrated in forming the desired cement composition, provides a composition which exhibits the desired inhibiting properties with respect to drying shrinkage. Alternatively, the n-butylcarbamate can be formed into an aqueous-alcoholic solution to be used as an admixture to be introduced into the cement composition at the job site or at the ready-mix batching plant.

The presently described admixture can be used to inhibit drying shrinkage in a variety of cement compositions, such as pastes (cement and water), mortars (cement, sand or other small particulate matter and water) and concretes (cement, sand, gravel and water). Suitable cement include ordinary portland cement (e.g. ASTM type I), special portland cement (high early strength portland cement and moderate heat portland cement), portland blast furnace slag cement, portland fly ash cement, as well as blended and high aluminous cement, for example.

In the preparation of a cement composition of the invention, aggregates such as gravel, sand, pumice and burned perlite may be used in known manners according to

- 5 -

the specific application. Further, conventional water-reducing agents, air-entraining agents, expansive agents, shrinkage-reducing agents other than the present invention, and other known admixtures for mortar or concrete may be jointly used.

Examples of known additives for mortar and concrete include hardening accelerators, such as metal chlorides (e.g. calcium chloride) or organic amines (e.g. triethanolamine), hardening retarders such as saccharides, starches, hydroxy carboxylic acids and glycerol; and corrosion inhibitors for reinforcing steel, such as sodium nitrite and calcium nitrite. The amount of such an optional additive added to cement is usually 0.1 - 5 wt %.

The amount of water to be added according to the invention is not critical as long as it is sufficient to effect hydration. The water/cement ratio is usually about 0.3 to 0.6, and preferably from 0.35 to 0.5.

It has been found that the present admixture provides a further enhanced cement composition when used in combination with a water-reducing agent. Although the carbamate described above can be used alone and provides both drying shrinkage inhibition and permits reduction in water, the composition when having both the subject carbamates and water-reducing agent provides enhanced properties. Examples of suitable, water-reducing agents are naphthalene sulfonate formaldehyde condensates, lignin sulfonates, melamine sulfonate formaldehydes, polyacrylates and the like. The amount of such water reducing agent to be used can range in from 0.05 to 5 weight percent based on the cement content of the formed composition.

- 6 -

The water-reducing agent can be added to the cement composition in ordinary manners, as part of any other admixture or with the present drying shrinkage control agent when added to the mixture of cement, aggregate and water.

The drying shrinkage inhibiting agent of the present invention can be added either to a dry cement or to a mixture of cement and other appropriate components forming the desired cement composition. Because the present admixture is either a solid or a low vapor pressure, high boiling liquid, it can be readily handled and stored without concern of evaporation and lack of potency at time of use. Thus, the present carbamate shrinkage reducing agent can be either dry mixed with the cement powder, or spray applied to the cement powder with further mixing. When the cement composition is a cement paste, the cement composition can be prepared by using a pre-mixed cement agent which is mixed with water, or a prescribed amount of the shrinkage-reducing agent is first dissolved in water-alcohol solution and then the solution is mixed with cement. If the cement composition is a mortar or concrete, a composition of the shrinkage reducing agent in an aqueous emulsion or dispersion may be first prepared and then mixed with cement and aggregate, or a given amount of the shrinkage-reducing agent is added to a mixture of cement, water, and aggregate while they are being stirred.

The cement composition may be cured using any of the atmospheric, wet air, water, and or heat-accelerated (steam, autoclave, etc.) curing techniques. If desired, two or more such techniques may be combined. The respective curing conditions may be the same as in conventional ones.

- 7 -

The present carbamate agents can be formed in known manners. For example, the agents can be formed from the related alcohol and urea at elevated temperatures in the presence of a catalyst such as heavy metal salts of weak organic acids or zinc or cobalt halide (chlorides). Alternately, the carbamate (especially tertiary carbamates) are formed with an alkali metal cyanate in the presence of trifluoroacetic acid, as taught in Organic Synthesis, Collective Volume 5, Page 162.

The present carbamates are formed in known manners. They can be formed from commodity chemicals by simple processing techniques. Further, the present shrinkage and crack control agents of the present invention are effective in low dosages of from about 1 to 10 weight percent based on the cement component of the cement composition. It is preferred to use from 1 to 5 and most preferably to use from 1 to 4 weight percent of the present agent based on cement content. The low dosage and ease of formation of the present agent provides a cost effective dry shrinkage and crack control agent for cement compositions. When the subject carbamate and water reducing agent are used in combination, the weight ratio of these components are 100:1 to 1:5 and preferably from 10:1 to 1:2.

The following example is given for illustrative purposes only and are not meant to be a limitation on the claims appended hereto. All parts and percentages are by weight unless otherwise indicated.

EXAMPLE

A micro-concrete composition composed of a mortar specifically designed to simulate concrete was formed

- 8 -

using portland cement, and fine aggregate of varying particle size. The composition was formed of the following mix:

<u>Components</u>	<u>Part by Weight</u>
Cement	100
Sand A	60
Sand B	54
Sand C	54
Sand D	102

5

10

Sand A had the following particle size distribution: 0.000% retained on 600 micron sieve size openings (reported as "0.00%/600"), 0.4%/425, 2%/300, 8%/212, 33%/150, 39%/106, 15%/75 and 2.6%/53.

15

Size B had a particle size of 150 to 1180 micron in accordance with ASTM C-778.

Sand C had a particle size of 600 to 1180 micron in accordance with ASTM C-778.

20

Sand D had the following particle size distribution: 0.00%/5000, 12.7%/2360, 55.7%/1700, 25.5%/1180, 5.4%/850 and 0.7%/600.

25

The various sand components were mixed together using a low speed mixer. The cement was then added with further mixing to form a substantially uniform blend. To this blend was added an aqueous dispersion of 3.16 parts n-butyl carbamate in 4.17 parts ethanol/37.83 parts water to provide a liquid/cement ratio of 0.42 and water to cement ratio of 0.39. Mixing was continued at low speed for 8 minutes and then poured into eight molds having dimensions of 25 x 25 x 285 mm. The specimens were cured for 24 hours in a chamber maintained at 100% relative humidity, demolded and then four (4) of the formed bars

30

- 9 -

were cured for 6 additional days at 100% relative humidity and 23°C and before being transferred to the environment chamber maintained at 50% relative humidity ("moist cure"). The remaining four (4) of the formed bars were cured at 50% relative humidity at 23°C ("dry cure") in order to measure drying shrinkage at differing conditions. Each of the bars was measured at regular intervals for changes in linear length using the comparator, described in ASTM C-490.

The results are given in Tables I & II below for dry cure and moist cure conditions, with respect to change in length (measured length minus original length divided by original length) with respect to time. Thus, a negative value connotes shrinkage in the length of the sample.

For comparative purposes, samples were formed in the same manner as described above except that the carbamate agent was omitted in one set of specimens ("Comp. I") and the carbamate and ethanol (equal amount replaced by H₂O) were deleted in a second set of specimens ("Comp. II"). The samples were tested in the same manner as described above and the results are given in Table I (for dry cure conditions) and Table II (for moist cure conditions).

TABLE I

Unrestrained Drying Shrinkage (Dry Cure)			
Length Change (x 10 ⁻⁶)			
Example	1 week	2 weeks	4 weeks
Carbamate	-266	-326	-349
COMP. I	-514	-596	-969
COMP. II	-459	-563	-591

- 10 -

TABLE II


Unrestrained Drying Shrinkage (Moist Cure)			
Length Change ($\times 10^{-6}$)			
Example	1 week	2 weeks	4 weeks
Carbamate	+33	-186	-240
COMP. I	+36	-338	-896
COMP. II	+33	-444	-667

The above data shows that samples which contained carbamate shrinkage reducing agent of the present invention exhibited substantially less drying shrinkage in comparison to samples without the subject carbamate (those merely with water or water/ethanol carrier mixture). Specifically, the dry cure samples with butyl carbamate exhibited 45% less drying shrinkage under dry cure conditions and about 60% less under moist cure conditions with respect to the sample prepared with water only.

- 11 -

WHAT IS CLAIMED:

- 1 1. A cement admixture comprising at least one compound of the formula:



- 5 wherein n is 1 or 2 and when n is 1, R is a C₃-C₈ alkyl group or a C₅-C₆ cycloalkyl group and when n is 2, R is a C₂-C₁₀ alkylene or an A(OA)_xOA group in which A is a C₂-C₃ alkylene and x is an integer of from 0 to 10; and at least one water reducing agent.

- 10 2. The admixture of Claim 1 wherein R is a C₄-C₆ alkyl and n is 1.

3. The admixture of Claim 1 wherein R is a butyl group and n is 1.

4. The admixture of Claim 1 wherein R is a C₄-C₈ alkylene and n is 2.

- 15 5. An improved cement comprising from 99 to 90 weight percent of a cement powder selected from a portland cement, blended cement or aluminous cement and substantially uniformly dispersed therein from 1 to 10 weight percent of at least one compound of the formula



- wherein n is 1 or 2 and when n is 1, R is a C₃-C₈ alkyl group or a C₅-C₆ cycloalkyl group and when n is 2, R is a C₂-C₁₀ alkylene or an A(OA)_xOA group in which A is a C₂-C₃ alkylene and x is an integer of from 0 to 10.

- 12 -

1 6. The product of Claim 5 wherein R is a butyl
group and n is 1.

7. The product of Claim 5 wherein R is $A(OA)_xOA$ in which each A represents an ethylene group, x is 0 or 1 and n is 2.

8. The product of Claim 5 which further contains at least one trialkanolamine.

9. The admixture of Claim 1 wherein R is a C₄-C₈ alkylene and n is 2.

10 10. An improved cement composition comprising cement, sand, aggregate and water and having substantially uniformly dispersed therein from 1 to 10 weight percent based on the cement of at least one compound of the formula:

15
$$\text{R}-\left[\text{O}-\overset{\text{O}}{\underset{\parallel}{\text{C}}}-\text{NH}_2 \right]_n$$
 wherein n is 1 or 2 and when n is 1, R is a C₃-C₈ alkyl group or a C₅-C₆ cycloalkyl group and when n is 2, R is a C₂-C₁₀ alkylene or an A(OA)_xOA group in which A is a C₂-C₃ alkylene and x is an integer of from 0 to 10.

20 11. The product of Claim 10 which further contains
a water reducing agent.

12. The product of Claim 10 wherein R is a butyl group and n is 1.

13. The product of Claim 11 wherein R is a butyl
25 group and n is 1.

- 13 -

1 14. The product of Claim 10 wherein R is $A(OA)_xOA$ in
which each A represents an ethylene group, x is 0 or 1
and n is 2.

5 15. The product of Claim 11 wherein R is $A(OA)_xOA$ in
which each A represents an ethylene group, x is 0 or 1
and n is 2.

16. The product of Claim 10 wherein R is a C_4-C_6
alkylene and n is 2.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 94/07948

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C04B24/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 411 583 (SYREMONT S.P.A.) 6 February 1991 see abstract; claims 1,2,6,9 see page 3, line 3 - page 4, line 49; example 6 ---	5,6
A	CHEMICAL ABSTRACTS, vol. 101, no. 20, 12 November 1984, Columbus, Ohio, US; abstract no. 176463w, 'Shrinkage reducing agents for cement' page 317 ; see abstract & JP,A,59 128 242 (SANYO CHEMICAL INDUSTRIES, LTD.) 24 July 1984 --- -/--	1,5,7

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

20 October 1994

Date of mailing of the international search report

03. 11. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Olsson-Norgren, S

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 94/07948

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	CHEMICAL ABSTRACTS, vol. 106, no. 20, 18 May 1987, Columbus, Ohio, US; abstract no. 161681v, G.I. GORCHAKOV ET AL 'Complex additive for mortar and concrete mixes' page 342 ; see abstract & SU,A,1 273 343 (STATE SCIENTIFIC-RESEARCH INSTITUTE FOR THE CEMENT INDUSTRY) 30 November 1986 ---	1,10,11
A	CHEMICAL ABSTRACTS, vol. 88, no. 12, 20 March 1978, Columbus, Ohio, US; abstract no. 78040z, M. POPOV ET AL 'Increased productivity of cement grinder using chemical additives' page 250 ; see abstract & TR. NAUCHNOIZSLED. INST. STROIT. MATER., vol.6, 1976, SOFIA pages 119 - 137 ---	1,5,8
A	FR,A,2 323 654 (INTERNATIONAL CONSTRUCTION PRODUCTS RESEARCH, INC.) 8 April 1977 see page 1, line 1 - line 26 see page 3, line 16 - line 34 see claims 1,3,9; example 2 ---	5,10
A	DATABASE WPI Section Ch, Week 7931, Derwent Publications Ltd., London, GB; Class A93, AN 79-57744B V.A. GOLUBEV ET AL & SU,A,629 193 (MINE ENRICHMENT) 7 September 1978 see abstract -----	1,10

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 94/07948

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0411583	06-02-91	NONE	
JP-A-59128242	24-07-84	JP-C- 1578987 JP-B- 2004544	13-09-90 29-01-90
SU-A-1273343	30-11-86	NONE	
FR-A-2323654	08-04-77	US-A- 4142909 BE-A- 846042 CA-A- 1069544 CA-A- 1070719 DE-A,C 2640389 GB-A- 1541129 JP-A- 52033921 NL-A- 7610031	06-03-79 31-12-76 08-01-80 29-01-80 24-03-77 21-02-79 15-03-77 15-03-77